Advanced Brazing Products Ltd.
Bidovce 316
04445 Bidovce, Slovakia
Tel +421 914 234 770
Email sales@advanced-brazing.com
Website https://www.advanced-brazing.com

Technical Data Sheet — ABP X92

ABP X92 · EN ISO 17672 CuP 182 · Copper-phosphorus brazing alloy

Field	Value
Product	ABP X92
Document ID	TDS.ABP.X92.EN.v1.1
Version	1.1
Effective	2026-10-10
Language	English
Family	Copper-phosphorus brazing alloy

1. Product Identification

Field	Value
EN ISO 17672	CuP 182
EN 1044	CP 201
DIN 8513	L-CuP8

EN 1044 is withdrawn and superseded by EN ISO 17672; designations shown for cross-reference.

2. Chemical Composition (wt %)

Element	Min.	Max.	Nominal
Copper (Cu)	–	–	92 (rem.)
Phosphorus (P)	7.5	8.1	8

3. Impurity Limits (max. wt %)

Field	Value
Aluminium (Al)	≤ 0.01
Bi	≤ 0.030
Cadmium (Cd)	≤ 0.010
Lead (Pb)	≤ 0.025
Zinc (Zn)	≤ 0.05
Zn + Cd	≤ 0.05
Total other	≤ 0.25

4. Physical Properties

Field	Value
Melting range	710–750 °C
Density	8 g/cm³
Tensile strength	250 N/mm²

Composition ranges per the referenced standard; physical data as published by Advanced Brazing Products.

5. Available Forms

Wire, rod, foil and paste

6. Safety

Refer to the Safety Data Sheet (SDS) for handling, personal protective equipment, ventilation and first-aid measures.

7. Sources

EN ISO 17672 / ISO 3677 designations and composition ranges. Advanced Brazing Products published product data (www.advanced-brazing.com).

Disclaimer

The information herein is believed to be accurate at the time of publication, but Advanced Brazing Products Ltd. makes no warranty with respect thereto. All sales are subject to the General Conditions of Sale and Delivery of Advanced Brazing Products Ltd.